

# PRODUCT DATA



## INJECTION GEL Epoxy Gel Adhesive

### PRODUCT DESCRIPTION

Five Star Injection Gel is a multi-purpose, two component, 100% solids, moisture insensitive, structural epoxy adhesive used in filling cracks up to 1/2 inch (13 mm). Five Star Injection Gel is a smooth, nonabrasive gel that can be pressure injected or hand applied. Five Star Injection Gel meets ASTM C 881 Types I, II, IV and V, Grade 3, Classes B & C; and also meets USDA specifications for use in food processing areas.

### ADVANTAGES

- VOC compliant
- Excellent adhesion to masonry, concrete, wood, steel and most structural materials
- Gel consistency ideal for vertical, overhead and non-mating surfaces
- Moisture insensitive
- Gel consistency ideal for vertical, overhead and non-mating surfaces
- Convenient 1:1 mixing ratio
- High strength

### USES

- Structural crack repairs to 1/4 inch (6 mm) width
- Anchoring of bolts, dowels, pins and special fasteners
- Pressure injection of cracks in structural concrete, masonry, wood and other substrates
- General purpose gel adhesive
- Surface repair of non-moving cracks on new or existing structures
- A pick-proof sealant around windows, doors, lock-ups and inside correctional facilities

### PACKAGING AND YIELD

Five Star Injection Gel is available in one gallon (3.7 liters) units yielding approximately 231 cubic inches of material.

### SHELF LIFE

Two years in original unopened packaging when stored in dry conditions at 45°F to 90°F (5°C - 35°C).

TYPICAL PROPERTIES AT 70°F (21°C)	
<b>Colour</b>	Gray
<b>Viscosity, ASTM D 2393</b>	Gel
<b>Flexural Strength, ASTM D 790</b>	5500 psi (38.0 MPa)
<b>Water Absorption, ASTM D 570</b>	0.10%
<b>Bond Strength, ASTM C 882</b>	
2 Day Cure	2600 psi (17.9 MPa)
14 Day Cure	4600 psi (31.7 MPa)
<b>Shrinkage, ASTM D 2566</b>	0.0007 in/in (mm/mm)
<b>Shear Strength, ASTM D 732</b>	3500 psi (24.2 MPa)
<b>Compressive Properties, ASTM D 695</b>	
Compressive Strength	10,000 psi (68.9 MPa)
Compressive Modulus	2.80 x 10 <sup>5</sup> psi (1930 MPa)
<b>Gel Time, ASTM C 881</b>	40 minutes

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.

## PLACEMENT GUIDELINES

- 1. SURFACE PREPARATION:** Surface must be clean and sound. For best results surfaces should be dry. Remove dust, laitance, grease, curing compounds, impregnations and waxes. Concrete may be sandblasted or prepared by other approved mechanical means. Steel should be sandblasted to an SSPC-SP6 commercial finish.
- 2. MIXING:** Material should be preconditioned to between 70°F and 80°F (21°C and 26°C) before using. Pre-mix each component thoroughly. Proportion equal parts by volume of Component A and Component B into a clean pail. Mix thoroughly for three minutes with a low speed drill (400-600 rpm) to avoid air entrapment. Do not mix more material than can be placed in 40 minutes at 70°F (21°C).
- 3. METHODS OF PLACEMENT:**
  - Pressure Injection:** Use automated equipment. Set appropriate injection ports based on system used. Seal ports and cracks with Five Star Injection Gel or Five Star RS Anchor Gel. When the epoxy adhesive seal has cured, inject Five Star Injection Gel with steady pressure until crack is filled.
  - Structural Adhesive:** Apply Five Star Injection Gel to the mating or non-mating prepared substrates. Work into the substrates for positive adhesion. Secure the bonded unit firmly into place until the adhesion has cured. Glue line should not exceed 1/8 inch (3 mm).
  - Anchor bolts, dowels, pins and plates:** Annular space around bolt should not exceed 1/8 inch (3 mm); depth of embedment is typically 10 to 15 times the bolt diameter. Place material in hole, starting from the rear to avoid air pockets. For best results, coat anchor with adhesive, insert and rotate slowly into hole.
  - Pick-proof sealant:** Use proper equipment to dispense an appropriate size bead around area being sealed. Tool material into joint to create seal.
- 4. CLEAN-UP:** Use an appropriate solvent to clean uncured material. Cured material can only be removed mechanically.

**NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY.** For more detailed placement procedures, refer to Design-A-Spec™ installation guidelines or call StonCor at (800) 263.3112.

## CONSIDERATIONS

- Minimum application temperature of substrate is 40°F (4°C) and rising. Low temperatures adversely affect consistency and strength gain.
- Cold temperatures lengthen gel time, hot temperatures decrease gel time.
- Do not thin with solvents.
- Do not inject moving or leaking cracks.
- Minimum age of concrete must be 21 to 28 days, depending on curing and drying conditions prior to application.
- For cracks over 1/2 inch (12 mm), call StonCor at (800) 263.3112.
- Material is vapour barrier after cure.

## CAUTION

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapours. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local sales representative, or call StonCor at (800) 263.3112.

**WARRANTY:** "FIVE STAR PRODUCTS INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

### Important:

StonCor believes the information contained here to be true and accurate as of the date of publication. StonCor makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

11/09

Rev. 11/09



95 Sunray Street • Whitby, Ontario • L1N 9C9 • Tel: 800.263.3112 • Fax: 800.786.6329

Vancouver • Calgary • Edmonton • Regina • Saskatoon • Winnipeg • Toronto • Ottawa • Halifax  
Saint John • St. John's • Montreal • Gatineau • Québec • Sherbrooke • Trois-Rivières • Chicoutimi

www.stoncorcpg.ca